

Mylar® polyester film
Only by DuPont Teijin Films

Mylar® 850 for Home Meal Replacement lidding



Application Description

Mylar® 850 for home meal replacement lidding

Benefits

- Permanent seal for tamper evidence
- Cook-in-the-pack convenience
- Excellent sealing through contamination


DuPont Teijin Films material selected and why

Mylar® 850 performs well at high speeds during the packing process, and allows freezer-to-oven convenience in both microwave and conventional ovens. When heat sealed Mylar® 850 produces a permanent tamper evident seal, other Mylar® grades which give peelable seals are also available.

Technical Information – Mylar® 850

Product Description

Mylar® 850 is a co-extruded, one side heat sealable polyester film. It can be heat sealed to itself and heat seals well to thermoformed APET/CPET trays and APET coated board. It also heat seals to various other substrates including PVdC, PVC, paper and aluminium foil, but will not seal to polyolefines. The plain (non heat-sealable) surface of Mylar® 850 exhibits the properties of a standard polyester film. Mylar® 850 is available in thicknesses of 15, 20 and 30 micron.



Typical Applications

Mylar® 850 is an excellent film for lidding to APET/CPET trays, either as a single web (Fig.1) or as part of a laminate (Fig. 2). Such packages are often used for dual ovenable ready meals. Mylar® 850 can also be used on Form-Fill-Seal machines and blister packs; its excellent aroma barrier properties make it ideal for packaging aromatic products such as air fresheners and toilet blocks.



Practical Information

Mylar® 850 has an exceptionally wide heat seal range, from 140°C to 220°C, with outstanding hot tack properties. Either fin seals or overlap seals may be made on conventional packaging equipment. The sealable surface of Mylar® 850 also acts as an excellent 'prime' for water-based latices. The film can thus be PVdC coated from an aqueous dispersion by converters without a primer to produce a high barrier laminating film. The plain surface of Mylar® 850 can be printed or metallised in the same way as plain polyester film, although the sealable surface makes handling of the film during conversion more critical. Mylar® 850 can withstand temperatures down to -70°C and food can be heated/cooked in this film at typical heating conditions of 220°C for 30 minutes. The heat seal surface of the film is normally wound on the inside of the reel (Mylar® 850i).

DuPont Teijin Films Contacts			
United Kingdom	Continental Europe	United States	Asia Pacific
DuPont Teijin Films (UK) Ltd	DuPont Teijin Films (Luxembourg) SA	DuPont Teijin Films	Teijin DuPont Films Japan Limited
PO Box 2002	BP-1681	1 Discovery Drive	Iino Bldg, 1-1, Uchisaiwai-Cho 2-Chome
Middlesbrough	L-1016 Luxembourg	PO Box 411	Chiyoda-Ku, Tokyo,
England TS90 8JF	Telephone +352 2616 4004	Hopewell VA 23860	100-8585, Japan
Telephone +44 (0) 1642 572000	Fax +352 2616 5000	Telephone +1 (800) 635 4639	Tel: +81-(0)3-3506-4243
Fax +44 (0) 1642 572075		Fax +1 (804) 530 9867	Fax: +81-(0)3-3506-4378
http://www.dupontteijinfilms.com			e-mail:packaging_films@gbp.dupont.com

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experiments. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont Teijin Films makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

Melinex®, Mylar®, and Cronar® are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetoron® are registered trademarks of Teijin Limited and are licensed to DuPont Teijin Films US, Limited Partnership. Teonex® is registered trademark of Teijin DuPont Films Japan Limited and licensed to DuPont Teijin Films U.S. Limited Partnership. The goods represented above are only examples of possible applications. DuPont Teijin Films does not imply that any DuPont Teijin Films products have been used in the manufacture of such goods. All third party trademarks and brand names are recognized. The goods represented above are only examples of possible applications. DuPont Teijin Films does not imply that any DuPont Teijin Films products have been used in the manufacture of such goods. All third party trademarks and brand names are recognized.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Teijin Films Medical Caution Statement", H-50102-1-DTF.

©2004 DuPont Teijin Films. All rights reserved